

LEVISO

- Luxurious dimout fabric with a colour matched reverse for a uniform appearance inside and out
- Oeko-Tex® Standard 100 certified, free from harmful substances
- Washable up to 60°
- Proven acoustic properties

APPLICATIONS



FABRIC PROPERTIES

	Dimout
	Polyester
	370 g/m ²
	0.80 mm
	295 cm
	300 cm

FEATURES / TECHNICAL PROPERTIES

	4-5
	Alpha-w = 0.75 / 0.90
	Flame retardant
	Fabric must be turned
	Fabric must be turned
	Fabric must be turned
	Oeko-Tex
	Special colours from 1'000 m

WASHING INSTRUCTIONS



FLAME RETARDANT

Class 1 (EN 13773)
 Class 1 (UNI 9176/77)
 M1 (NF P 92-503/5/7)
 Type B (BS 5867-2)



Leviso
OPTICAL AND SOLAR COEFFICIENTS ($\pm 5\%$, DIN EN 410)

Colour	T_V	T_S	R_S	A_S	T_{UV}	F_C	g_{tot}
1	1.9	2.2	62.0	35.8	0.1	0.52	0.38
2	1.9	2.2	62.0	35.8	0.1	0.52	0.38
3	1.9	2.2	62.0	35.8	0.1	0.52	0.38
5	1.9	2.2	62.0	35.8	0.1	0.52	0.38
7	0.0	1.0	38.8	60.2	0.0	0.67	0.48
8	0.0	1.0	40.9	58.1	0.0	0.66	0.47
9	0.1	1.2	45.9	52.9	0.0	0.63	0.45
11	0.0	1.2	39.5	59.3	0.0	0.67	0.48
12	0.2	1.2	54.2	44.6	0.0	0.57	0.41
14	0.1	1.2	45.9	52.9	0.0	0.63	0.45
15	0.1	1.2	45.9	52.9	0.0	0.63	0.45
18	0.2	1.2	54.2	44.6	0.0	0.57	0.41
19	0.1	1.1	49.7	49.2	0.0	0.60	0.43
21	0.3	1.4	61.4	37.2	0.0	0.53	0.38
23	1.9	2.2	62.0	35.8	0.1	0.52	0.38
24	0.3	1.4	61.4	37.2	0.0	0.53	0.38
25	0.1	1.2	45.9	52.9	0.0	0.63	0.45
26	0.0	1.0	40.9	58.1	0.0	0.66	0.47
28	0.0	1.0	40.9	58.1	0.0	0.66	0.47

T_V Visible light transmission

R_S Solar reflectance

T_{UV} UV transmission


g_{tot} Total g-value

T_S Solar transmission


A_S Solar absorption

F_C Shading factor


$F_C + g_{tot}$: Value calculated with glass: $0.72 / U_g = 1.6 \text{ W/m}^2 \text{ K}$, DIN EN 13363-1

Leviso


1



2



3




5



7




8



9




11




12



14



15



18



19



21



23



24



25



26



28

Colours shown are not binding